

Fecha de Alta

10-09-2008

Versión

9 - 04/03/2020


FAMILY REVESTIMIENTOS DE FACHADAS

LINE REVESTIMIENTOS LISOS

DESCRIPTION AND NATURE

Smooth coating, offering good whiteness, resistance and coverage. For use on white works

USAGES

Outdoors/Indoors

Cement

Facades

Wood after varnished

Cement mortars

Porous brick

PROPERTIES

Waterproof

Working smoothness

Light & climatic resistant colours

Does not present tacking

Does not turn yellow

Strong resistance to the atmospheric factors

Does not spread flame

Elasticity enough to resist the normal structural movements

Easy application

Water steam transpirable

- AFNOR NFT 36005 Family I clase 7b2. COV=40 g/l. DTU 59.1 Clase D2 Norm p84-403 c - CLASSIFIED

TECHNICAL CHARACTERISTICS

Referencia Color NEVADA FACHADAS LISO BLANCO

Finish Smooth matt

Specific weight 1,62± 0,05 kg/l

Viscosity 124 +/- 15 PO

Solids in volume 46± 1

Solids in weight 68± 1

VOC Cat. c/BA 75/40 (2007/2010):0,69 g/l

Aproximated performance by coat 4-8 m²/L

Dry to touch (20° C HR: 60%): 30 min-1h. Washing 25-30 days

Dry to repaint (20° C HR: 60%): 4-6 h

Colours White 103 and colours Nevada chart.
For manual tinting, up to 5% colorant maximum
SURFACE PREPAIRING
French norm DTU 59.1
New surfaces

Cement mortar:

- 1.Wait till complete drying of product (30 days minimum).
- 2.Remove off any efflorescences by abrasive jet.
- 3.Neutralize alkaline surfaces.

Fecha de Alta

10-09-2008

Versión

9 - 04/03/2020

4. Extremely polished surfaces should be sanpapered to open pores.
5. Remove off any foreing products or remains.
6. Very damaged surfaces should be fixed with suitable product.
7. Cover surface imperfections with Plastmont Exteriores (See Family 6 to help you choose the most suitable product to prepare surfaces).

-Plaster:

1. Wait till complete drying of product (20% max. Moisture level).
2. Remove off any foreign product or product remains.
3. Remove off any efflorescences.
4. Use a sealant or matt paste to regulate surface absorption.
5. Extremely polished surfaces should be sandpapered to open pore.
6. Very damaged surfaces should be fixed with suitable product (See Family 6.)
7. Cover surface imperfections with plaster or putty (See Family 6 to help you choose the most suitable product to prepare surfaces).

Restoring and maintenance

1. Remove off old paint completely.
2. Brilliant surfaces should be matted to ensure good adherence.
3. Check paint type and anchoring in painted surfaces to avoid incompatibilities. Remove off any dust or dirt before painting.
4. Cover surface imperfections with suitable putty of plaster (See Family 6 to help you choose the most suitable product to prepare surfaces).
5. Mildewed surfaces should be treated with Montolimp.

WAY OF USE

Application Notes

Shake product until perfectly homogenized.

For the first coat application, this product should be dilluted depending on porosity and surface condition.

Finish with one or more coats slightly dilluted until surface is totally covered.

Do not apply product at temperatures below 5°C.

Do not apply in the sun or at extreme humid conditions.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	10-20%
Roller	10-20%
Air-less gun	10-30%
Air-mix gun	10-30%
Aerographic gun	10-30%
Low pressure turbo	10-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Support with mould			
MAX	Montolimp + Fijamont, Emulsión Fijadora	Nevada Fachadas Liso	Nevada Fachadas Liso
STD	Montolimp		Nevada Fachadas Liso
Old paintings in bad state			
MAX	Eliminar + Fijamont, Emulsión Fijadora	Nevada Fachadas Liso	Nevada Fachadas Liso
STD	Eliminar + Nevada Fachadas Liso diluido		Nevada Fachadas Liso
Old painting in good state			
MAX	Nevada Fachadas Liso diluido	Nevada Fachadas Liso	Nevada Fachadas Liso

Fecha de Alta

10-09-2008

Versión

9 - 04/03/2020

STD	Nevada Fachadas Liso diluido	Nevada Fachadas Liso
------------	------------------------------	----------------------

Support weak

MAX	Fijamont, Emulsión Fijadora	Nevada Fachadas Liso	Nevada Fachadas Liso
------------	-----------------------------	----------------------	----------------------

STD	Nevada Fachadas Liso diluido	Nevada Fachadas Liso
------------	------------------------------	----------------------

Masonry mortar

MAX	Fijamont, Emulsión Fijadora	Nevada Fachadas Liso	Nevada Fachadas Liso
------------	-----------------------------	----------------------	----------------------

STD	Nevada Fachadas Liso diluido	Nevada Fachadas Liso
------------	------------------------------	----------------------

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

15 L