

MONTOSPORT PISCINAS AL AGUA



FAMILY PRODUCTOS PARA USO ESPECIFICO
LINE INSTALACIONES DEPORTIVAS

DESCRIPTION AND NATURE

Water-based acrylic paint for protecting and painting concrete swimming pools. With an anti-mould and anti-algae effect.

USAGES

Outdoors/Indoors

Cement

Pools

PROPERTIES

Surface leveling

Fungus and seaweed protector

- Water resistant

Alacalynity resistance

- Good adhesion

The product may become discoloured depending on the type and concentration of the disinfectant used.

- Strong resistance to the atmospherical factors

- Does not spead flame

- Good yield

- Good applicability

- For both freshwater and saltwater pools

TECHNICAL CHARACTERISTICS

Referencia Color MONTOSPORT PISCINAS AL AGUA AZUL

Finish Semi-matt

Specific weight 1,21± 0,05 kg/l

Viscosity 141 +/- 20 PO

Solids in volume 41± 1

Solids in weight 53± 1

Aproximated performance by coat 5-9 m²/L

Dry to touch (20°C HR: 60%): 10-30 min. Fill pool: 8 days

Dry to repaint (20°C HR: 60%): 24 h

Colours Blue-183, White 102

SURFACE PREPAIRING

New surfaces

Cement mortars:

1. Wait until fully hardened (min. 30 days).
2. Clean off possible efflorescence with an abrasive jet.
3. Neutralise alkaline surfaces.
4. For polished surfaces: sand down to open the grain.
5. Clean any unusual products from the base.
6. Fix crumbling bases using fixative emulsion or Fijamont.
7. Fill in any defects/flaws in the base.

Plaster:

1. Wait until the plaster is dry (maximum 20% humidity).

Fecha de Alta

12-11-2008

Versión

13 - 04/07/2022

2. Clean any unusual products from the base.
3. Clean off possible efflorescence with an abrasive jet.
4. Control the absorbency of the base using a sealer, fixative or a diluted coat of the same product.
5. For polished surfaces: sand down to open the grain.
6. Fix crumbling bases using fixative emulsion or Fijamont.
7. Fill in any defects/flaws in the base (see family 6)

Restoring and maintenance

- 1 - Completely remove any old or loose paint.
- 2 - Dull down glossy surfaces to ensure good adhesion.
- 3 - On painted bases, check the solidity and anchorage of the paint and the type of paint in order to avoid potential incompatibilities. Remove dust and dirt before repainting.
- 4 - Fill in any defects in the base using plaster.
- 5 - Walls with mould, treat first with fungicide (Montolimp).

WAY OF USE

Application notes

- Stir the product until perfectly homogenised.
- Dilute the product according to the porosity and state of the base on the first coat.
- Finish with one or two slightly diluted coats, until the base has full coverage.
- Adhesion should be checked between coats of paint on old paint given that it is usual to repaint swimming pools regularly, therefore adhesion between coats may be greater than the adhesion of the old paints on the case and this could cause peeling of the old coats of paint.

This product is resistant to chlorine and chlorine derivatives if concentration is within the limits indicated in RD 742/2013, 27th of September.

For any other treatment (flocculants, algacides ...), check with the supplier the possibility to be used in painted pools.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	10-20%
Roller	10-20%
Air-less gun	5-20%
Air-mix gun	5-20%
Aerographic gun	10-30%
Low pressure turbo	10-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Old paintings in bad state			
MAX			
STD	Eliminar+Montosport al agua diluido		Montosport piscinas al agua
Old painting in good state			
MAX			
STD	Montosport al agua diluido		Montosport piscinas al agua
Wood			
MAX	No aplicable		
STD			
Cement			
MAX	Fijador, Emulsión Fijadora	Montosport piscinas al agua	Montosport piscinas al agua
STD	Montosport piscinas al agua diluido		Montosport piscinas al agua

MONTOSPORT PISCINAS AL AGUA



Support weak

MAX	Fijador, Emulsión Fijadora	Montosport piscinas al agua diluido	Montosport piscinas al agua
STD	Fijador, Emulsión Fijadora	Montosport piscinas al agua	Montosport piscinas al agua

Plaster

MAX No aplicable

STD

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

4 L, 12 L