### 501950

MASSIMA+





#### MONTÓ Massima ples Constantine Constantine

## FAMILY PAREDES Y TECHOS / SISTEMAS TINTOMÉTRICOS

LINE LINEA MONTOMIX

### DESCRIPTION AND NATURE

Water-based enamel for walls and ceilings. Used for decorating smooth, high quality surfaces thanks to its silky feel, finish and levelling. Maximum durability due to its resistance to stains and scratches, even in intense colours. Ideal product for professional application, faster, more effective, profitable high-performance projects.

### USAGES

Outdoors/Indoors Walls and ceilings Cement mortars Brick Plaster Dripping effect Drywall (gypsum plasterboard): fibreboard

### PROPERTIES



Security Certification for Toys according to Standard EN 71-3:2013 + A1:2014
Minimum splattering
Good retouching
Gloss level: deep matt (according to UNE-EN 13300, at 85° reflectance < 5)</li>
Euroclasses certification as per norm UNE EN 13501-1:07:B-s1-d0
-Washability: Class 1 (according to Standard UNE-EN 13300)
Opacity: Class 1 for a performance of 5.5 m2/litre (according to Standard UNE-EN 13300). This information may vary depending on the colour chosen.
smooth finish
With antimould additive

### TECHNICAL CHARACTERISTCS

Referencia ColorMASSIMA+ BLANCOFinishDeep mattSpecific weight1,32± 0,05 kg/lViscosity55 +/- 10 POSolids in volume46± 1Solids in weight59± 1VOCCat. a/BA 75/30 (2007/2010):0,10 g/lAproximated performance by coat14-16 m²/LDry to touch(20°C HR 60%): 15-30 minDry to repaint(20°C HR 60%): 2-3 hoursColoursWhite BL, IN and TR bases Tintometric System Colours.		
Specific weight1,32± 0,05 kg/lViscosity55 +/- 10 POSolids in volume46± 1Solids in weight59± 1VOCCat. a/BA 75/30 (2007/2010):0,10 g/lAproximated performance by coat14-16 m²/LDry to touch(20°C HR 60%): 15-30 minDry to repaint(20°C HR 60%): 2-3 hoursColoursWhite BL, IN and TR bases	Referencia Color	MASSIMA+ BLANCO
Viscosity55 +/- 10 POSolids in volume46± 1Solids in weight59± 1VOCCat. a/BA 75/30 (2007/2010):0,10 g/lAproximated performance by coat14-16 m²/LDry to touch(20°C HR 60%): 15-30 minDry to repaint(20°C HR 60%): 2-3 hoursColoursWhite BL, IN and TR bases	Finish	Deep matt
Solids in volume46± 1Solids in weight59± 1VOCCat. a/BA 75/30 (2007/2010):0,10 g/lAproximated performance by coat14-16 m²/LDry to touch(20°C HR 60%): 15-30 minDry to repaint(20°C HR 60%): 2-3 hoursColoursWhite BL, IN and TR bases	Specific weight	1,32± 0,05 kg/l
Solids in weight59±1VOCCat. a/BA 75/30 (2007/2010):0,10 g/lAproximated performance by coat14-16 m²/LDry to touch(20°C HR 60%): 15-30 minDry to repaint(20°C HR 60%): 2-3 hoursColoursWhite BL, IN and TR bases	Viscosity	55 +/- 10 PO
VOC       Cat. a/BA 75/30 (2007/2010):0,10 g/l         Aproximated performance by coat       14-16 m²/L         Dry to touch       (20°C HR 60%): 15-30 min         Dry to repaint       (20°C HR 60%): 2-3 hours         Colours       White BL, IN and TR bases	Solids in volume	46± 1
Aproximated performance by coat     14-16 m²/L       Dry to touch     (20°C HR 60%): 15-30 min       Dry to repaint     (20°C HR 60%): 2-3 hours       Colours     White BL, IN and TR bases	Solids in weight	59± 1
Dry to touch       (20°C HR 60%): 15-30 min         Dry to repaint       (20°C HR 60%): 2-3 hours         Colours       White BL, IN and TR bases	VOC	Cat. a/BA 75/30 (2007/2010):0,10 g/l
Dry to repaint (20°C HR 60%): 2-3 hours Colours White BL, IN and TR bases	Aproximated performance by coat	14-16 m²/L
Colours White BL, IN and TR bases	Dry to touch	(20°C HR 60%): 15-30 min
BL, IN and TR bases	Dry to repaint	(20ºC HR 60%): 2-3 hours
	Colours	BL, IN and TR bases

### SURFACE PREPAIRING



MASSIMA+

Fecha de Alta 11-02-2019 Versión 5 - 04/03/2020



#### New surfaces

- Cement and concrete mortars:
- 1. Wait until fully set (min. 30 days).
- 2. Clean any efflorescence with a jet washer.
- 3. Neutralize alkaline surfaces.
- 4. Sand polished surfaces to create a rougher surface.
- 5. Clean the surface to remove foreign products.
- 6. Set crumbly substrates with Fixer Emulsion or Fijamont.
- 7. Fill in defects in the substrate (see family 6)

Plaster, plaster-covered brick:

- 1. Wait until it is completely dry (max. 20% humidity).
- 2. Clean the surface to remove foreign products.
- 3. Clean any efflorescence with a jet washer.
- 4. Regulate surface absorption with sealer, fixer, or a diluted coat of the same product
- 5. Sand polished surfaces to create a rougher surface
- 6. Set crumbly substrates with Fixer Emulsion or Fijamont.
- 7. Fill in defects in the substrate (see family 6)

Plasterboard partition walls:

- 1. Carry out a general sanding of the joints and putty fixing areas.
- 2. Then, clean them to ensure the substrate is free of dust, grease and other contaminants.
- 3. For application on coloured boards that tend to generate stains, apply Montoplac Stain-Resistant Sealer.

#### **Restoring and maintenance**

- 1. Completely remove old paint that is in poor condition or that is poorly-adhered.
- 2. Glossy surfaces should be thinned out to ensure good adhesion.
- 3. On painted surfaces, check that the paint is solid and well-adhered. Its condition must be assessed, in order to avoid possible incompatibilities. Dust and dirt must also be eliminated before repainting.
- 4. Apply filler (Plasmont) to any defects on the surface.
- 5. Pre-treat mouldy walls using Montolimp.

### WAY OF USE

#### **Application Notes**

- Remove the product until perfectly homogeneous.
- Apply on clean and dry surfaces, removing dirt with soapy water. In the case of extreme dirt, it is advisable to use degreasing agents or cleaning detergents.
- Apply in accordance with requirements marked in the attached application table.
- Do not apply the product at temperatures below 5° nor on surfaces exposed to strong sunshine.
- Maintain good ventilation conditions during the drying time.
- Do not apply whilst the relative humidity is above 80%.
- For a perfect finish we recommend applying with a spray gun, but if you do use a roller it should be one designed for varnishing.
- Do not wash for the first 24 days.
- Clean tools with water immediately after use.
- Never apply it outdoors if there is an imminent risk of rain, and avoid excessively wet days.
- For spraying with Airless equipment, use 15 to 23 inch nozzles, pressure  $\approx$  150 bar.

# Solvent for dilution and cleaning Water

Way of use	Aproximate dilution
Painting brush	0-10%
Roller	0-10%
Air-less gun	5-10%
Low preasure turbo	5-10%

### 501950

MASSIMA+

Fecha de Alta 11-02-2019 Versión 5 - 04/03/2020



### SYSTEM

Proce	dures depending of surface type					
	Primer	Intermedium	Finish			
New v	vork					
MAX	Fijador	Massima+	Massima+			
STD	Massima+ Diluido		Massima+			
Inner painted old work in good state						
MAX	Massima+ Diluido	Massima+	Massima+			
STD	Massima+ Diluido		Massima+			
Inner painted old work in good state						
MAX	Eliminar+ Fijador	Massima+	Massima+			
STD	Eliminar+ Massima+		Massima+			
Drywall (gypsum plasterboard)						
MAX	Massima+ Diluido	Massima+	Massima+			
STD	Massima+ Diluido		Massima+			

### SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

### NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between  $5^{\circ}$  and  $35^{\circ}$ C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adecuate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

### PACKINGS

0.75 L, 4 L, 12 L