

Fecha de Alta

04-04-2014

Versión

4 - 20/02/2018



FAMILY TRATAMIENTOS SUELO Y METALES / SISTEMAS TINTOMÉTRICO
LINE ACRILICAS AGUA

DESCRIPTION AND NATURE

Water-soluble paint for floors with modified acrylic emulsion base. Quick-drying, with excellent adhesion and hardness on cement-type surfaces. Ideal for painting floors indoors and outdoors, for road markings, on asphalt media in good condition, terraces, driveways, etc.

USAGES

Outdoor/Indoor
 Cement
 Moulded concrete
 Cement
 Concrete
 Cement mortars

PROPERTIES

Adherence
 Strongness
 Surface protection
 Odourless when dry
 Resistance to friction and hits
 Anti-dust
 Do not cause suppuration in asphaltic surfaces
 Washable
 Easily applicable
 - Water-based
 Drying fast
 - U.V. resistant
 - Easy to repaint

TECHNICAL CHARACTERISTICS

Referencia Color	PAVIMONT ACQUA BLANCO
Finish	Semi-matt
Specific weight	1,25± 0,05 kg/l
Viscosity	100 +/- 10 KU
Solids in volume	41± 1
Solids in weight	55± 1
VOC	Cat. i/BA 140/140 (2007/2010): 19,99 g/l
Aproximated performance by coat	6-9 m ² /L
Dry to touch	10 - 30 min.
Dry to repaint	1 - 2 h.
Colours	White, Grey 189, Red 152, Blue Zone 184, Green 128, Daffodil Yellow 130, Base BL, Base TR.

SURFACE PREPAIRING

New surfaces

Masonry surfaces (cement and derivatives):

1. Treat these surfaces in the usual way, removing saltpetre, excess moisture and efflorescence.
2. Treat the surface to achieve the desired porosity.

Fecha de Alta

04-04-2014

Versión

4 - 20/02/2018

3. Remove foreign products and/or residues.

Restoring and maintenance

Clean, mend and fill any parts in poor condition.

Remove flaking or poorly adhered paint.

If necessary, sand for better adhesion and to get the right degree of porosity.

WAY OF USE**Application Notes**

A spot test before application is always advisable.

Stir the product until perfectly blended.

Do not apply the product at high temperatures or on surfaces exposed to strong insolation.

Humidity of flooring: maximum of 4% measured at a depth of 2cm.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Brush, Roller	0 - 15 %
Aerographic gun	10 - 25 %
Air-less gun	0 - 10 %

SYSTEM**Procedures depending of surface type**

	Primer	Intermedium	Finish
Cement			
MAX	PAVIMONT ACQUA	PAVIMONT ACQUA	BARNIZ PAVIMONT ACQUA
STD	PAVIMONT ACQUA		PAVIMONT ACQUA

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L, 15 L