



FAMILY TRATAMIENTOS DE LA MADERA / SISTEMAS TINTOMÉTRICOS
LINE PROTECTORES AL AGUA (P. A.)

DESCRIPTION AND NATURE

Lasure-type transparent varnish for protecting interior and exterior wood, with UV protectors.

USAGES

Outdoors/Indoors

For maximum protection, finish in colour.

Recommended previously created with primer

Specially recommended for mountain and coastal areas

PROPERTIES

Penetration power

Provides open pore finish

- Do not apply white media, you can amarillarlos slightly, but does not alter the properties of the product.

Does not turn yellow

no need of sanding, but easy to do once dried

recommended number of coats : 2-3 coats over new wood, 1-2 coats as maintenance

No cracking at all

Does not form blisters

Water steam transpirable

Odourless when dry

- Endures brusque changes in the weather

- Flexible

- Microporous

- Highlights the wood's natural grain

- U.V. resistant

- May be used as a base when diluted, thus nourishing the wood

TECHNICAL CHARACTERISTICS

Referencia Color	MONTOXYL LASURE ACQUA MATE
Finish	Matt
Specific weight	0,97± 0,05 kg/l
Viscosity	180 +/- 30 SG
Solids in volume	23± 1
Solids in weight	26± 1
VOC	Cat. e/BA 150/130 (2007/2010): 130,00 g/l
Aproximated performance by coat	10-16 m ² /L
Dry to touch	(20°C HR: 60%): 2-4 h. Total: 12-24 h
Dry to repaint	(20°C HR: 60%): 12-24 h
Colours	Base: TR 900 Cromiservice and Montomix (max 5%) systems. Montotinte universal or water (max: 5%)

SURFACE PREPAIRING

New surfaces

New wood

MONTOXYL LASURE ACQUA MATE

- Surface should be free of any foreign products or remains.
- Apply on wood with less than 20% moisture content.
- Apply on wood in good condition, dry and free of grease and dust.
- Sandpaper and eliminate any remains in joints and mechanical faults.
- Old wood should be previously sanded and dust-free.
- Applying MONTOXYL LASURE ACQUA MATE in the conditions described and following the restoration and maintenance indications, the product can provide the highest resistance protection to wood for up to seven years. Depends on the location/area, conditions and stress to which the varnished wood is subjected.

Restoring and maintenance

Painted or varnished surfaces:

- If they have been varnished with Montoxyl Color, remove off foreign remains, or areas in bad condition, sandpaper slightly, brush any resulting dust and proceed as per new wood.
- If they have been varnished with close pore varnishes such as Barniz Sintetico Universal Mat (ref. 1350), Satinado (Ref. 1360 or Brillante (Ref. 1370), Barniz Velero (ref. 1380), Barniz Alta Montaña (ref. 1385) or similar, apply a stripping product such as Quitamont Universal (ref. 3510) or use a mechanical system if any blisters or cracks have arisen and proceed as per new wood. If surfaces are in good condition, sandpaper slightly, brush any resulting dust and proceed as per new wood.
- If they have been varnished with cellulose or polyetherane based varnishes, apply a stripping product such as Quitamont Universal (ref. 3510) or use a mechanical system and proceed as per new wood.
- If they have been painted with synthetic enamels (such as Montosintetic, Marisma, Luxatin or similar), apply a stripping product such as Quitamont Universal (ref. 3510) or use a mechanical system and proceed as per new wood.
- ????

WAY OF USE

Application Notes

Stir product completely.

- Only apply on clean and dry surfaces.
- Dilute product according to application system recommendations.
- Surface should be sanded previously to ensure good product penetration and wood levelling.
- It is recommended that the condition and appearance of the surfaces of items previously varnished with MONTOXYL LASURE ACQUA MATE should be reviewed periodically in order to maintain full protective effectiveness. If deterioration is found, due to knocks and/or scratches, etc., it is recommended to clean and sand the damaged area and re-varnish with MONTOXYL LASURE ACQUA MATE.
- For the first coat, it is recommended to prime with Fondo Lasure Acqua. Montoxyl Fondo is also suitable.
- Do not apply at high temperatures or on overheated surfaces exposed to sunshine.
- Keep room well ventilated while product is drying.
- Do not apply when moisture content is over 80%.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	fondo: 10-30%
Roller	10-30%
Air-less gun	30-50%
Air-mix gun	30-50%
Aerographic gun	10-30%
Low pressure turbo	10-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New wood/old outdoor			
MAX	Al exterior: Anticarcomas Klearxyl Di	Montoxyl Fondo Color	Lasure Acqua Color
STD	Al exterior: Anticarcomas Klearxyl Di	Lasure Acqua Color	Lasure Acqua Incoloro/Color

varnished or painted wood

Fecha de Alta

04-07-2007

Versión

11 - 27/02/2020

MAX	Al exterior: Decapar+ Anticarcomas Klearxyl Di	Montoxyl Fondo Color	Lasure Acqua Color
STD	Al exterior: Decapar+ Anticarcomas Klearxyl Di	Lasure Acqua Color	Lasure Acqua Incoloro/Color

Old/New interior Wood

MAX	Lasure Acqua o Montoxyl Fondo	Lasure Acqua	Lasure Acqua
STD	Lasure acqua o Montoxyl Fondo		Lasure Acqua

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adecuate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L



FAMILY LINE

DESCRIPTION AND NATURE

Lasure-type transparent varnish for protecting interior and exterior wood, with UV protectors.

USAGES

PROPERTIES

Penetration power

Provides open pore finish

- Do not apply white media, you can amarillarlos slightly, but does not alter the properties of the product.

Does not turn yellow

no need of sanding, but easy to do once dried


recommended number of coats : 2-3 coats over new wood, 1-2 coats as manteinance

No cracking at all

Does not form blisters

Water steam transpirable

Odourless when dry



- Endures brusque changes in the weather
- Flexible
- Microporous
- Highlights the wood's natural grain
- U.V. resistant
- May be used as a base when diluted, thus nourishing the wood

TECHNICAL CHARACTERISTICS

Referencia Color	
Finish	Matt
Specific weight	0,97 ± 0,05 kg/l
Viscosity	180 +/- 30 SG
Solids in volume	23 ± 1
Solids in weight	26 ± 1
VOC	Cat. e/BA 150/130 (2007/2010): 130,00 g/l
Aproximated performance by coat	10-16 m ² /L
Dry to touch	(20°C HR:60%): 2-4 h. Total: 12-24 h
Dry to repaint	(20°C HR:60%): 12-24 h
Colours	Base: TR 900 Cromiservice and Montomix (max 5%) systems. Montotinte universal or water (max: 5%)

SURFACE PREPAIRING

New surfaces

New wood

- Surface should be free of any foreign products or remains.
- Apply on wood with less than 20% moisture content.
- Apply on wood in good condition, dry and free of grease and dust.
- Sandpaper and eliminate any remains in joints and mechanical faults.
- Old wood should be previously sandpapered and dust-free.
- Applying MONTOXYL LASURE ACQUA MATE in the conditions described and following the restoration and maintenance indications, the product can provide the highest resistance protection to wood for up to seven years. Depends on the location/area, conditions and stress to which the varnished wood is subjected.

Restoring and maintenance

Painted or varnished surfaces:

- If they have been varnished with Montoxyl Color, remove off foreign remains, or areas in bad condition, sandpaper slightly, brush any resulting dust and proceed as per new wood.
- If they have been varnished with close pore varnishes such as Barniz Sintetico Universal Mat (ref. 1350), Satinado (Ref. 1360 or Brillante (Ref. 1370), Barniz Velero (ref. 1380), Barniz Alta Montaña (ref. 1385) or similar, apply a stripping product such as Quitamont Universal (ref. 3510) or use a mechanical system if any blisters or cracks have arisen and proceed as per new wood. If surfaces are in good condition, sandpaper slightly, brush any resulting dust and proceed as per new wood.
- If they have been varnished with cellulose or polyetherane based varnishes, apply a stripping product such as Quitamont Universal (ref. 3510) or use a mechanical system and proceed as per new wood.
- If they have been painted with synthetic enamels (such as Montosintetic, Marisma, Luxatin or similar), apply a stripping product such as Quitamont Universal (ref. 3510) or use a mechanical system and proceed as per new wood.
- ????


WAY OF USE

Application Notes

Stir product completely.

- Only apply on clean and dry surfaces.
- Dilute product according to application system recommendations.
- Surface should be sandpapered previously to ensure good product penetration and wood levelling.
- It is recommended that the condition and appearance of the surfaces of items previously varnished with MONTOXYL LASURE ACQUA MATE should be reviewed periodically in order to maintain full protective effectiveness. If deterioration is found, due to

MONTOXYL LASURE ACQUA MATE



knocks and/or scratches, etc., it is recommended to clean and sand the damaged area and re-varnish with MONTOXYL LASURE ACQUA MATE.

- For the first coat, it is recommended to prime with Fondo Lasure Acqua. Montoxyl Fondo is also suitable.

-Do not apply at high temperatures or on overheated surfaces exposed to sunshine.

-Keep room well ventilated while product is drying.

-Do not apply when moisture content is over 80%.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	fondo: 10-30%
Roller	10-30%
Air-less gun	30-50%
Air-mix gun	30-50%
Aerographic gun	10-30%
Low pressure turbo	10-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New wood/old outdoor			
MAX	Al exterior: Anticarcomas Klearxyl Di	Montoxyl Fondo Color	Lasure Acqua Color
STD	Al exterior: Anticarcomas Klearxyl Di	Lasure Acqua Color	Lasure Acqua Incoloro/Color
varnished or painted wood			
MAX	Al exterior: Decapar+ Anticarcomas Klearxyl Di	Montoxyl Fondo Color	Lasure Acqua Color
STD	Al exterior: Decapar+ Anticarcomas Klearxyl Di	Lasure Acqua Color	Lasure Acqua Incoloro/Color
Old/New interior Wood			
MAX	Lasure Acqua o Montoxyl Fondo	Lasure Acqua	Lasure Acqua
STD	Lasure acqua o Montoxyl Fondo		Lasure Acqua

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

501340


Fecha de Alta

04-07-2007

Versión

11 - 27/02/2020

MONTOXYL LASURE ACQUA MATE



PACKINGS

0.75 L, 4 L