

# MONTOPOL BLANCO MATE 59 NA



**FAMILY** TRATAMIENTOS DE LA MADERA / SISTEMAS TINTOMÉTRICOS  
**LINE** ACABADOS POLIU. FIG. (L. Y P.)

## DESCRIPTION AND NATURE

Two-component matt white polyurethane varnish, with good whiteness, coverage, feel and levelling. Resistant to yellowing.

## USAGES

Indoors

Wood treatment

Product for exclusive use in industries regulated by Directive 2010/75 Chapter V.

## PROPERTIES

- Adherence
- Optimal applicability
- High solid contents
- Strongness
- Elasticity
- Fast drying
- Odourless when dry
- Good coverage
- Good whiteness

## TECHNICAL CHARACTERISTICS

Referencia Color	MONTOPOL BLANCO MATE 59
Mixture relation	2 (Montopol): 1 (Cat.)
Finish	Matt
Specific weight	1,14 ± 0,05 kg/l
Viscosity	220 +/- 20 SG
Solids in volume	37 ± 1
Solids in weight	52 ± 1
Aproximated performance by coat	10-14 m <sup>2</sup> /L
Dry to touch	(20°C HR: 60%): 15-20min
Colours	NCS, RAL

## SURFACE PREPARING

### New surfaces

- New wood:
- The base must be free from foreign materials and/or waste matter.
- Apply to wood with a moisture content of less than 12%.
- Apply over a recommended base

### Restoring and maintenance

- Varnished or painted wood:
- If in doubt, remove the previous varnish, lacquer or enamel.
- Apply over a recommended base

## WAY OF USE

### Application notes

- Stir product completely.
- Mixed up within given proportions.
- Do not apply product in layers too thick which may exceed 90 wet micres per coat.
- Ensure that CATALIZADOR MONTOPOL MS is totally transparent before performing mixture.

### Solvent for dilution and cleaning

Solvent 1410

Way of use	Aproximate dilution
Painting brush	0-5%
Air-less gun	5-10%
Air-mix gun	5-10%
Aerographic gun	0-20%
Low pressure turbo	5-10%

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Old/New interior Wood</b>			
<b>MAX</b>	Montopol fondo+Cat. MS	Montopol fondo+Cat. MS	Montopol blanco mate 59+Cat. NA
<b>STD</b>	Montopol fondo+Cat. MS		Montopol blanco 59+Cat. NA
<b>Painted or varnished wood (closed pore) indoor</b>			
<b>MAX</b>	Decapar+Montopol fondo+Cat. MS	Montopol fondo+Cat. MS	Montopol blanco mate 59+Cat. NA
<b>STD</b>	Decapar+Montopol fondo+Cat. MS		Montopol blanco mate 59+Cat. NA
<b>Open pore varnished wood</b>			
<b>MAX</b>	Montopol fondo+Cat. MS	Montopol fondo+Cat. MS	Montopol blanco mate 59+Cat. MS
<b>STD</b>	Montopol fondo+Cat. MS		Montopol blanco mate 59+Cat. MS

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Product of exclusive use for premises regulated under RD 117/2003 or 1999/13/CE regulations

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances.As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

5 L, 25 L



## FAMILY LINE

## DESCRIPTION AND NATURE

Two-component matt white polyurethane varnish, with good whiteness, coverage, feel and levelling. Resistant to yellowing.

## USAGES

## PROPERTIES

- Adherence
- Optimal applicability
- High solid contents
- Strongness
- Elasticity
- Fast drying
- Odourless when dry
- Good coverage
- Good whiteness

## TECHNICAL CHARACTERISTICS

Referencia Color	
Mixture relation	2 (Montopol): 1 (Cat.)
Finish	Matt
Specific weight	1,14± 0,05 kg/l
Viscosity	220 +/- 20 SG
Solids in volume	37± 1
Solids in weight	52± 1
Aproximated performance by coat	10-14 m <sup>2</sup> /L
Dry to touch	(20°C HR: 60%): 15-20min
Colours	NCS, RAL

## SURFACE PREPARING


### New surfaces

- New wood:
- The base must be free from foreign materials and/or waste matter.
- Apply to wood with a moisture content of less than 12%.
- Apply over a recommended base

### Restoring and maintenance

- Varnished or painted wood:
- If in doubt, remove the previous varnish, lacquer or enamel.
- Apply over a recommended base

# MONTOPOL BLANCO MATE 59 NA



## WAY OF USE

### Application notes

- Stir product completely.
- Mixed up within given proportions.
- Do not apply product in layers too thick which may exceed 90 wet micres per coat.
- Ensure that CATALIZADOR MONTOPOL MS is totally transparent before performing mixture.

### Solvent for dilution and cleaning

Solvent 1410

Way of use	Aproximate dilution
Painting brush	0-5%
Air-less gun	5-10%
Air-mix gun	5-10%
Aerographic gun	0-20%
Low pressure turbo	5-10%

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Old/New interior Wood</b>			
<b>MAX</b>	Montopol fondo+Cat. MS	Montopol fondo+Cat. MS	Montopol blanco mate 59+Cat. NA
<b>STD</b>	Montopol fondo+Cat. MS		Montopol blanco 59+Cat. NA
<b>Painted or varnished wood (closed pore) indoor</b>			
<b>MAX</b>	Decapar+Montopol fondo+Cat. MS	Montopol fondo+Cat. MS	Montopol blanco mate 59+Cat. NA
<b>STD</b>	Decapar+Montopol fondo+Cat. MS		Montopol blanco mate 59+Cat. NA
<b>Open pore varnished wood</b>			
<b>MAX</b>	Montopol fondo+Cat. MS	Montopol fondo+Cat. MS	Montopol blanco mate 59+Cat. MS
<b>STD</b>	Montopol fondo+Cat. MS		Montopol blanco mate 59+Cat. MS

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Product of exclusive use for premises regulated under RD 117/2003 or 1999/13/CE regulations

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

501615


Fecha de Alta

16-10-2007

Versión

12 - 23/07/2020

# MONTOPOL BLANCO MATE 59 NA



## PACKINGS

5 L, 25 L