



PU TOPCOAT CLEAR - [GLOSS] Product No. PT 2299

[Standard Grade

Standard grade two components Polyurethane clear gloss Topcoat, formulated with solid content combined with fast drying, very good transparency, flow, and leveling characteristics, provide the excellent equalization of the gloss effect. Combined with the high mechanical resistant and soft slippery touch that enhances the overall beauty and feasibility of the finishing product.

USES

For interior use on all furnishings as wardrobes, closet, paneling, doors, windows frame, and casting, etc. The overall characteristics such as extensibility, Gloss effect equalization, transparency and resistance to polishing have been developed to the maximum which in turn enables the product to have almost unlimited possibilities in the furniture industry.

CHARACTERISTICS

Properties

- Excellent Covering - Very Good Transparency

Very Good Leveling - Very Good Flow Fast Drying - Brilliant Finish

Appearance : Gloss

Flash point : 21°C

Drying Time

Dust Free : 20 min.

To Touch : 60 min. at 25°C Interval Coats : 2 hrs. at 25°C Deep Drying : 24 hrs. at 25°C Polish able : 48 hrs. at 25°C

SURFACE PREPARATION

All timber species must be fully aged with a moisture content of less than 15%. Surface must be dry, clean and free from contaminations. Natural oil or gum must be removed by solvent cleaning.

To obtain optimum surface finish sand the wood properly in the same direction of the wood grain, utilize sanding paper no. [100] for surface leveling. Apply one coat PU Sanding Sealer, then after drying, utilize paper no. [220] to create smoothness to the substrate then utilize paper no. [400] to achieve perfection of substrate, as is adequate sanding and removal of dust prior to application of first coat. Control the compatibility of Stains eventually used.

Date Revised: 01st Jan 2012





PU TOPCOAT CLEAR - [GLOSS] Product No. PT 2299

PRODUCT PREPARATION

CA	T	Λ	I \	$^{\prime}$ c	т
CH	۱I.	м	L ĭ	ು	

by weight		by volume	
50%	CP037	50%	

Pot Life 6 hrs. @25°C

Stir product well with a flat paddle. Add the correct quantity of hardener and stir till homogeneous. Thin to required viscosity. For details of spray equipment contact Ritver Technical Services Department.

Dilution

It comes ready to use, no need to add thinner. In case of high humidity climate add 5-10% [TP222] PU retardant thinner. We can add 30% thinner TP297 in case of hot weather.

APPLICATION METHODS

Depends on the finishes required but in general an appropriate rate is 150 gr / sq. m. The number of coats depends on the surface preparation the porosity of the substrate, and the finish required.

Following Treatments

utilize nozzle 1.8 - 2 mm at 3-4 ATM/bar. For details of By spray gun:

spray equipment contact Ritver Technical Services Department.

By Curtain Coater: it is recommended to control the viscosity during application by adding PU

Thinner to balance the evaporation of solvents.

CLEANING

Cleaning

Clean all tools and equipment immediately after use with [TC010] Tool Cleaner.

PACKING & STORAGE

Available in 5Ltr. 25Ltr.

Store in a cool and well ventilated place. Keep away from direct sunlight. Minimum one year in unopened container, stored in a cool and dry condition at 25°C.

SAFETY & FLAMMABLE

This material is flammable and must not be exposed to naked flames.

Use only in well ventilated areas. In case of insufficient ventilation during application, wear suitable respiratory equipment. Do not breathe vapor / spray. In case of contact with eyes, rinse immediately with plenty of sweet water and seek medical advice. In case of contact with skin, wash immediately with soap and water or a recognized skin cleanser.

Keep away from sources of ignition. No Smoking. Keep out of reach of children.

Date Revised: 01st Jan 2012