

PU TOPCOAT CLEAR – [MATT] Product No. **PT 25XX**

[Anti-scratch Grade]

Anti-scratch grade two components Polyurethane Topcoat, formulated with solid content combined with fast drying, good transparency, flow, and leveling characteristics, provide the excellent equalization of the matt or semi matt effect. Combined with the high mechanical resistant and soft slippery touch that enhances the overall beauty and feasibility of the finishing product.

USES

For interior use on all furnishings as wardrobes, closet, paneling, doors, windows frame, and casting, etc. The overall characteristics such as extensibility, Matt or Semi Matt effect equalization, transparency and resistance to polishing have been developed to the maximum which in turn enables the product to have almost unlimited possibilities in the furniture industry

CHARACTERISTICS

Properties

- Anti-scratch Grade
- Very Good Leveling
- Fast Drying
- Very Good Transparency
- Very Good Flow

Available in the following Shades

- PT2500 DM 6% [±1]
- PT2510 MT 12% [±3]
- PT2530 SM 30% [±5]
- PT2550 SG 50% [±5]
- PT2570 GL 70% [±5]

Appearance	: Matt or Semi Matt
Color	: Transparent
Specific gravity	: 0.970 Kg/lit [±0.025]
Weight Solids	: Approx. 35% [± 2]
Weight Solids blended	: Approx. 33% [± 2]
Flash point	: 21°C
Drying Time	
Dust Free	: 15 min.
To Touch	: 35 min. at 25°C
Interval Coats	: 3 hrs. at 25°C
Deep Drying	: 24 hrs. at 25°C

PU TOPCOAT CLEAR – [MATT] Product No. **PT 25XX**

[Anti-scratch Grade]

SURFACE PREPARATION

All timber species must be fully aged with a moisture content of less than 15%. Surface must be dry, clean and free from contaminations. Natural oil or gum must be removed by solvent cleaning.

To obtain optimum surface finish sand the wood properly in the same direction of the wood grain, utilize sanding paper no. [100] for surface leveling. Apply one coat PU Sanding Sealer, then after drying, utilize paper No.[220] to create smoothness to the substrate , then utilize paper No.[400

] to achieve perfection of substrate, as is adequate sanding and removal of dust prior to application of first coat. Control the compatibility of Stains eventually used.

PRODUCT PREPARATION

CATALYST		
by weight 50%	CP006	by volume 50%

Pot Life 3 hrs. at 25°C

Stir product well with a flat paddle. Add the correct quantity of hardener and stir till homogeneous. Thin to required viscosity. For details of spray equipment contact Ritver Technical Services Department.

Dilution

Utilize [TP292] PU Thinner depending on the application system used. In general 20 -30% thinner is added to achieve an application viscosity. This is suitable for spraying.

For Curtain coater 20% Thinner is added to achieve an application viscosity. In case of high humidity climate add 5-10% [TP222] PU retardant thinner.

APPLICATION METHODS

Depends on the finishes required but in general an appropriate rate is 130 gr / sq. m. The number of coats depends on the surface preparation the porosity of the substrate, and the finish required.

Following Treatments

By spray gun: utilize nozzle 1.8 – 2 mm at 3-4 ATM/bar. For details of spray equipment contact Ritver Technical Services Department.

By Curtain Coater: it is recommended to control the viscosity during application by adding PU Thinner to balance the evaporation of solvents.

PU TOPCOAT CLEAR – [MATT] Product No. **PT 25XX** [Anti-scratch Grade]

CLEANING

Cleaning

Clean all tools and equipment immediately after use with [TC010] Tool Cleaner.

PACKING & STORAGE

Available in 5Ltr, 25Ltr.

Store in a cool and well ventilated place. Keep away from direct sunlight. Minimum one year in unopened container, stored in a cool and dry condition at 25°C.

SAFETY & FLAMMABLE

This material is flammable and must not be exposed to naked flames.

Use only in well ventilated areas. In case of insufficient ventilation during application, wear suitable respiratory equipment. Do not breathe vapor / spray. In case of contact with eyes, rinse immediately with plenty of sweet water and seek medical advice. In case of contact with skin, wash immediately with soap and water or a recognized skin cleanser.

Keep away from sources of ignition. No Smoking. Keep out of reach of children.